



# **Taseko Prosperity Gold-Copper Project**

## **Appendix 3-7-MM**

CLIENT : SRK Consulting  
 PROJECT : Taseko  
 CEMI Project # : 0697  
 Test : Modified Acid-Base Accounting  
 Date : November 7-10, 2006

DRAFT COPY

Drillhole (m)	From (m)	To (m)	Interval (m)	Sample ID	Paste pH	CO2 %	CaCO3 NP	S(T) %	S(SO4) %	S(S-2) %	AP	NP	NP*	Net NP	Fizz Test	NP/AP
92-071	78	86	8	COMP 51388-51391	7.3	3.77	85.7	0.53	0.02	0.51	15.9	61.8	51.8	45.9	Moderate	3.9
92-071	94	100	6	COMP 51396-51398	7.2	0.91	20.7	0.76	0.02	0.74	23.1	31.6	21.6	8.5	Moderate	1.4
92-071	100	104	4	COMP 51399-51400	6.9	2.36	53.6	0.33	<0.01	0.33	10.3	60.6	50.6	50.3	Strong	5.9
92-071	110	118	8	COMP 51404-51407	7.1	1.57	35.7	2.32	1.63	0.69	21.6	35.4	25.4	13.8	Moderate	1.6
92-071	118	123	5	COMP 51408-51410	7.1	3.89	88.4	0.34	0.08	0.26	8.1	79.5	69.5	71.4	Strong	9.8
92-071	126	132	6	COMP 51412-51414	7.3	2.69	61.1	2.41	0.88	1.53	47.8	58.3	48.3	10.5	Strong	1.2
92-071	132	138	6	COMP 51415-51417	7.1	1.88	42.7	2.25	1.12	1.13	35.3	50.5	40.5	15.2	Strong	1.4
92-071	156	162	6	COMP 51427-51429	7.1	0.45	10.2	1.52	1.06	0.46	14.4	13.7	3.7	-0.7	Slight	1.0
92-071	162	168	6	COMP 51430-51432	7.2	0.56	12.7	2.2	1.6	0.6	18.8	16.7	6.7	-2.1	Slight	0.9
92-071	168	174	6	COMP 51433-51435	7.0	0.44	10.0	2.19	1.59	0.6	18.8	14.0	4.0	-4.8	Slight	0.7
92-071	174	182	8	COMP 51436-51439	7.1	1.54	35.0	2.3	1.53	0.77	24.1	31.9	21.9	7.8	Moderate	1.3
92-071	184	192	8	COMP 51441-51444	7.0	0.64	14.5	2.04	1.74	0.3	9.4	17.6	7.6	8.2	Slight	1.9
92-071	192	200	8	COMP 51445-51448	6.6	0.55	12.5	2.1	1.61	0.49	15.3	9.5	-0.5	-5.8	Slight	0.6
92-071	200	206	6	COMP 51449-51451	6.9	0.96	21.8	2.32	1.74	0.58	18.1	18.2	8.2	0.1	Slight	1.0
92-071	206	212	6	COMP 51452-51454	7.0	2.88	65.5	1.92	1.32	0.6	18.8	46.6	36.6	27.9	Slight	2.5
92-071	214	220	6	COMP 51456-51458	6.9	1.76	40.0	1.52	1.22	0.3	9.4	30.6	20.6	21.2	Slight	3.3
92-071	220	226	6	COMP 51459-51461	7.2	6.2	140.9	1.11	1.24	-0.13	0.3	106.2	96.2	110.3	Moderate	340
92-071	226	232	6	COMP 51462-51464	7.2	4.2	95.5	1.76	1.28	0.48	15.0	71.8	61.8	56.8	Moderate	4.8
92-071	232	238	6	COMP 51465-51467	7.3	4.27	97.0	2.35	1.44	0.91	28.4	33.3	23.3	4.9	Moderate	1.2
92-071	238	244	6	COMP 51468-51470	7.2	2.45	55.7	2.24	1.49	0.75	23.4	51.0	41.0	27.6	Moderate	2.2
92-071	244	250	6	COMP 51471-51473	7.2	0.96	21.8	2.59	1.77	0.82	25.6	22.1	12.1	-3.5	Moderate	0.9
92-071	250	256	6	COMP 51474-51476	7.2	1.53	34.8	2.26	1.42	0.84	26.3	35.3	25.3	9.1	Slight	1.3
92-071	256	262	6	COMP 51477-51479	7.4	2.06	46.8	2.18	0.97	1.21	37.8	47.4	37.4	9.6	Moderate	1.3
92-071	262	268	6	COMP 51480-51482	7.3	0.94	21.4	2.09	1.1	0.99	30.9	23.4	13.4	-7.5	Slight	0.8
92-071	268	270	2	COMP 51483	7.5	1.13	25.7	0.85	0.5	0.35	10.9	28.4	18.4	17.5	Moderate	2.6
92-071	270	278	8	COMP 51484-51486-51487	7.3	1.14	25.9	1.62	0.96	0.66	20.6	28.9	18.9	8.3	Slight	1.4
92-071	278	284	6	COMP 51488-51490	7.2	1.09	24.8	2.44	1.41	1.03	32.2	34.1	24.1	1.9	Slight	1.1
92-071	284	290	6	COMP 51491-51493	7.0	3.36	76.4	1.66	1.03	0.63	19.7	73.6	63.6	53.9	Slight	3.7
92-071	290	296	6	COMP 51494-51496	7.0	2.03	46.1	1.71	1.2	0.51	15.9	55.0	45.0	39.1	Slight	3.5
92-071	296	302	6	COMP 51497-51499	7.3	2.15	48.9	1.65	0.88	0.77	24.1	51.8	41.8	27.7	Slight	2.2
92-071	304	310	6	COMP 51501-51503	7.4	1.35	30.7	1.96	0.99	0.97	30.3	35.3	25.3	5.0	Slight	1.2
92-071	310	316	6	COMP 51504-51506	7.2	0.89	20.2	2.29	1.29	1.0	31.3	20.0	10.0	-11.3	Slight	0.6
92-071	316	322	6	COMP 51507-51509	7.3	1.09	24.8	1.64	0.82	0.82	25.6	27.0	17.0	1.4	Slight	1.1
92-071	322	328	6	COMP 51510-51512	7.1	0.39	8.9	4.28	1.29	2.99	93.4	13.5	3.5	-79.9	Slight	0.1
92-071	328	332	4	COMP 51513-51514	7.2	0.84	19.1	3.48	0.97	2.51	78.4	23.3	13.3	-55.1	Slight	0.3
92-071	334	340	6	COMP 51516-51518	7.1	0.45	10.2	3.33	1.45	1.88	58.8	14.2	4.2	-44.6	Slight	0.2
92-071	340	346	6	COMP 51519-51521	7.0	0.26	5.9	3.09	1.59	1.5	46.9	15.9	5.9	-31.0	Slight	0.3
92-071	346	352	6	COMP 51522-51524	7.2	0.36	8.2	4.66	1.17	3.49	109.1	16.4	6.4	-92.7	Slight	0.2
92-071	352	358	6	COMP 51525-51527	7.2	0.74	16.8	4.31	1.12	3.19	99.7	21.8	11.8	-77.9	Slight	0.2
92-071	358	362	4	COMP 51528-51529	7.1	0.5	11.4	4.48	1.38	3.1	96.9	16.7	6.7	-80.2	Slight	0.2
92-082	69.39	78	8.61	COMP 72095-72098	7.3	1.32	30.0	1.24	0.02	1.22	38.1	25.6	15.6	-12.5	Moderate	0.7
92-082	80	86	6	COMP 72100-72102	7.8	2.08	47.3	1.14	0.02	1.12	35.0	39.7	29.7	4.7	Moderate	1.1
92-082	86	92	6	COMP 72103-72105	8.0	3.78	85.9	2.38	0.02	2.36	73.8	65.9	55.9	-7.8	Slight	0.9
92-082	92	98	6	COMP 72106-72108	7.6	4.44	100.9	3.53	0.03	3.5	109.4	88.9	78.9	-20.5	Moderate	0.8
92-082	98	104	6	COMP 72109-72111	8.3	2.67	60.7	1.59	0.02	1.57	49.1	59.8	49.8	10.7	Strong	1.2
92-082	104	108	4	COMP 72112-72113	7.8	8.29	188.4	1.78	0.01	1.77	55.3	148.8	138.8	93.5	Moderate	2.7
92-082	110	116	6	COMP 72115-72117	7.8	5.47	124.3	2.63	0.03	2.6	81.3	105.9	95.9	24.7	Slight	1.3
92-082	116	122	6	COMP 72118-72120	8.2	6.2	140.9	1.76	0.02	1.74	54.4	110.6	100.6	56.2	Moderate	2.0
92-082	122	128	6	COMP 72121-72123	7.9	5.21	118.4	1.21	0.02	1.19	37.2	82.8	72.8	45.6	Moderate	2.2
92-082	128	134	6	COMP 72124-72126	8.3	0.72	16.4	0.46	0.02	0.46	14.4	24.6	14.6	10.2	Slight	1.7
92-082	134	138	4	COMP 72127-72128	7.7	0.27	6.1	0.46	0.02	0.44	13.8	15.9	5.9	2.2	Slight	1.2
92-082	140	146	6	COMP 72130-72132	7.6	0.37	8.4	1.42	0.03	1.39	43.4	17.2	7.2	-26.2	Slight	0.4
92-082	146	152	6	COMP 72133-72135	7.7	0.44	10.0	0.87	0.02	0.85	26.6	18.7	8.7	-7.9	Slight	0.7
92-082	152	158	6	COMP 72136-72138	7.0	1.11	25.2	1.34	0.02	1.32	41.3	30.6	20.6	-10.7	Moderate	0.7
92-082	158	164	6	COMP 72139-72141	7.6	1.73	39.3	1.34	0.02	1.32	41.3	41.4	31.4	0.1	Moderate	1.0
92-082	164	170	6	COMP 72142-72144	7.3	0.53	12.0	1.24	0.04	1.2	37.5	22.4	12.4	-15.1	Slight	0.6
92-082	172	178	6	COMP 72146-72148	7.5	0.74	16.8	1.37	0.03	1.34	41.9	25.2	15.2	-16.7	Slight	0.6
92-082	178	184	6	COMP 72149-72151	7.6	0.57	13.0	1.03	0.02	1.01	31.6	20.8	10.8	-10.8	Slight	0.7
92-082	184	189.6	5.6	COMP 72152-72154	7.6	1.94	44.1	1.52	0.02	1.5	46.9	46.0	36.0	-0.9	Moderate	1.0
92-082	189.6	198	8.4	COMP 72155-72158	7.4	5.43	123.4	2.37	0.02	2.35	73.4	112.0	102.0	38.6	Moderate	1.5
92-082	200	208	8	COMP 72160-72163	7.7	2.85	64.8	1.48	0.02	1.46	45.6	71.9	61.9	26.3	Moderate	1.6
92-082	208	212	4	COMP 72164-72165	7.4	2.72	61.8	0.23	0.01	0.22	6.9	65.5	55.5	58.6	Moderate	9.5
92-082	212	218	6	COMP 72166-72168	7.3	4.31	98.0	2.52	0.44	2.08	65.0	114.9	104.9	49.9	Moderate	1.8
92-082	218	224	6	COMP 72169-72171	7.3	2.02	45.9	2.6	0.8	1.8	56.3	55.6	45.6	-0.6	Moderate	1.0
92-082	224	230	6	COMP 72172-72173	7.2	1.53	34.8	2.83	0.85	1.98	61.9	53.1	43.1	-8.8	Moderate	0.9
92-082	230	236	6	COMP 72175-72177	7.4	1.31	29.8	2.01	0.68	1.33	41.6	31.4	21.4	-10.2	Slight	0.8
92-082	236	242	6	COMP 72178-72180	7.3	3.64	82.7	2.29	0.83	1.46	45.6	75.5	65.5	29.9	Slight	1.7
92-082	242	248	6	COMP 72181-72183	7.3	0.9	20.5	2.8	0.9	1.9	59.4	27.0	17.0	-32.4	Slight	0.5

Note:

AP = Acid potential in tonnes CaCO3 equivalent per 1000 tonnes of material. AP is determined from calculated sulphide sulphur content: S(T) - S(SO4).

NP = Neutralization potential in tonnes CaCO3 equivalent per 1000 tonnes of material.

NET NP = NP - AP

Carbonate NP is calculated from CO2 originating from carbonates and is expressed in kg CaCO3/tonne.

Total S by Leao

Sulphate-sulphur by 25% HCl leach with gravimetric finish.

CO2 by HCl leach.

PROJECT : Taseko  
 SRK Project # : 1CT 013.000  
 CEMI Project # : 0697  
 Test : Modified Acid-Base Accounting  
 Date : March 8-19, 2007

DRAFT COPY

Sample ID	From (m)	To (m)	Paste pH	CO2 %	CaCO3 NP	S(T) %	S(SO4) %	S(S-2) %	AP	NP	NP*	NP/AP	NP*/AP	Carb NP/AP	Net NP	Fizz Test
96-219 COMP 22-28	22	28	8.38	4.44	100.9	0.93	0.08	0.85	26.6	84.0	74.0	3.2	2.8	3.8	57.4	Strong
96-219 COMP 28-34	28	34	9.29	5.76	130.9	0.91	0.11	0.8	25.0	108.8	98.8	4.4	4.0	5.2	83.8	Moderate
96-219 COMP 34-40	34	40	8.11	4.58	104.1	1.25	0.08	1.17	36.6	76.3	66.3	2.1	1.8	2.8	39.7	Moderate
96-219 COMP 40-46	40	46	8.81	5.02	114.1	0.39	0.01	0.38	11.9	70.0	60.0	5.9	5.1	9.6	58.1	Moderate
96-219 COMP 46-52	46	52	8.92	9.13	207.5	0.08	<0.01	0.08	2.5	139.0	129.0	55.6	51.6	83.0	136.5	Moderate
96-219 COMP 52-58	52	58	8.74	5.94	135.0	0.14	<0.01	0.14	4.4	89.8	79.8	20.5	18.2	30.9	85.4	Moderate
96-219 COMP 58-64	58	64	8.65	12.25	278.4	0.85	<0.01	0.85	26.6	174.5	164.5	6.6	6.2	10.5	147.9	Moderate
96-219 COMP 64-70	64	70	8.85	9.72	220.9	0.48	<0.01	0.48	15.0	153.5	143.5	10.2	9.6	14.7	138.5	Moderate
96-219 COMP 70-74	70	74	8.75	6.27	142.5	0.47	0.02	0.45	14.1	121.3	111.3	8.6	7.9	10.1	107.2	Moderate
96-219 COMP 74-80	74	80	8.64	4.84	110.0	1.41	0.01	1.4	43.8	98.3	88.3	2.2	2.0	2.5	54.6	Moderate
96-219 COMP 80-86	80	86	8.67	5.21	118.4	0.9	<0.01	0.9	28.1	109.5	99.5	3.9	3.5	4.2	81.4	Strong
96-219 COMP 86-92	86	92	8.47	5.24	119.1	1.55	0.01	1.54	48.1	92.0	82.0	1.9	1.7	2.5	43.9	Strong
96-219 COMP 92-98	92	98	8.92	2.28	51.8	0.98	0.02	0.96	30.0	61.8	51.8	2.1	1.7	1.7	31.8	Moderate
96-219 COMP 98-104	98	104	8.39	2.05	46.6	0.45	<0.01	0.45	14.1	59.8	49.8	4.3	3.5	3.3	45.7	Moderate
96-219 COMP 104-110	104	110	8.99	2.76	62.7	0.54	<0.01	0.54	16.9	70.8	60.8	4.2	3.6	3.7	53.9	None
96-224 COMP 16-22	16	22	8.80	0.05	1.1	<0.02	<0.01	0.01	0.3	11.3	1.3	37.7	4.3	3.8	11.3	None
96-224 COMP 22-28	22	28	8.71	0.07	1.6	0.02	<0.01	0.02	0.6	10.3	0.3	16.5	0.5	2.5	9.7	None
96-224 COMP 28-34	28	34	8.21	0.05	1.1	0.02	<0.01	0.02	0.6	19.5	9.5	31.2	15.2	1.8	18.9	None
96-224 COMP 34-40	34	40	8.23	0.04	0.9	0.02	<0.01	0.02	0.6	22.8	12.8	36.5	20.5	1.5	22.2	None
96-224 COMP 40-46	40	46	8.12	0.03	0.7	<0.02	<0.01	0.01	0.3	19.5	9.5	65.0	31.7	2.3	19.5	None
96-224 COMP 46-52	46	52	8.80	0.04	0.9	0.02	<0.01	0.02	0.6	15.0	5.0	24.0	8.0	1.5	14.4	None
96-224 COMP 52-58	52	58	8.04	0.05	1.1	0.02	<0.01	0.02	0.6	8.3	-1.7	13.3	0.0	1.8	7.7	None
96-224 COMP 58-64	58	64	7.14	0.04	0.9	0.03	<0.01	0.03	0.9	40.5	30.5	43.2	32.5	1.0	39.6	Slight
96-224 COMP 64-70	64	70	7.25	0.05	1.1	0.03	<0.01	0.03	0.9	38.8	28.8	41.4	30.7	1.2	37.9	Slight
96-224 COMP 70-76	70	76	7.08	0.06	1.4	0.03	<0.01	0.03	0.9	15.8	5.8	16.9	6.2	1.5	14.9	Slight
96-224 COMP 76-82	76	82	7.08	0.06	1.4	<0.02	<0.01	0.01	0.3	41.3	31.3	137.7	104.3	4.5	41.3	None
96-224 COMP 82-88	82	88	7.28	0.03	0.7	0.03	<0.01	0.03	0.9	20.0	10.0	21.3	10.7	0.7	19.1	None
96-224 COMP 88-94	88	94	6.60	0.01	0.2	0.53	0.05	0.48	15.0	15.8	5.8	1.1	0.4	0.0	0.8	None
96-224 COMP 94-100	94	100	6.94	0.03	0.7	0.37	0.03	0.34	10.6	22.5	12.5	2.1	1.2	0.1	11.9	None
96-224 COMP 100-106	100	106	7.08	0.04	0.9	0.32	0.02	0.3	9.4	18.5	8.5	2.0	0.9	0.1	9.1	None
96-230 COMP 90.53-96	90.53	96	8.33	0.88	20.0	0.05	0.01	0.04	1.3	21.3	11.3	17.0	9.0	16.0	20.1	Moderate
96-230 COMP 96-102	96	102	8.25	1.62	36.8	0.02	<0.01	0.02	0.6	28.8	18.8	46.1	30.1	58.9	28.2	Moderate
96-230 COMP 102-108	102	108	8.42	6.49	147.5	0.3	<0.01	0.3	9.4	81.0	71.0	8.6	7.6	15.7	71.6	Moderate
96-230 COMP 108-114	108	114	8.31	5.28	120.0	2.13	0.03	2.1	65.6	83.5	73.5	1.3	1.1	1.8	17.9	Moderate
97-235 COMP 30-36	30	36	7.54	0.3	6.8	0.03	<0.01	0.03	0.9	13.3	3.3	14.2	3.5	7.3	12.4	None
97-235 COMP 36-42	36	42	7.83	0.23	5.2	<0.02	<0.01	0.01	0.3	6.0	0.1	20.0	0.3	17.4	6.0	Slight
97-235 COMP 42-48	42	48	7.85	0.98	22.3	<0.02	<0.01	0.01	0.3	26.3	16.3	87.7	54.3	74.2	26.3	Slight
97-235 COMP 48-54	48	54	7.85	3.73	84.8	0.18	<0.01	0.18	5.6	64.8	54.8	11.5	9.7	15.1	64.8	Moderate
97-235 COMP 54-60	54	60	8.02	5.7	129.5	0.02	<0.01	0.02	0.6	85.8	75.8	137.3	121.3	207.3	85.8	Moderate
97-235 COMP 60-66	60	66	8.06	11.86	269.5	0.02	<0.01	0.02	0.6	201.8	191.8	322.9	306.9	431.3	201.8	Strong
97-235 COMP 66-72	66	72	7.95	7.78	176.8	0.04	<0.01	0.04	1.3	108.6	98.6	86.9	78.9	141.5	108.6	Moderate
97-235 COMP 72-78	72	78	7.88	7.62	173.2	0.1	<0.01	0.1	3.1	109.3	99.3	35.0	31.8	55.4	109.3	Moderate
97-235 COMP 78-84	78	84	8.06	5.04	114.5	0.22	<0.01	0.22	6.9	108.3	98.3	15.8	14.3	16.7	108.3	Moderate
97-235 COMP 84-90	84	90	7.89	4.04	91.8	0.45	<0.01	0.45	14.1	75.9	65.9	5.4	4.7	6.5	75.9	Moderate
97-235 COMP 90-96	90	96	7.88	6.16	140.0	0.28	<0.01	0.28	8.8	85.6	75.6	9.8	8.6	16.0	85.6	Moderate
97-235 COMP 96-102	96	102	8.11	7.05	160.2	0.15	<0.01	0.15	4.7	117.1	107.1	25.0	22.8	34.2	117.1	Moderate
97-254 COMP 68-74	68	74	8.33	10.09	225.3	0.27	<0.01	0.27	8.4	139.8	129.8	16.6	15.4	27.2	139.8	Moderate
97-254 COMP 74-80	74	80	7.77	8.97	203.9	0.78	<0.01	0.78	24.4	139.1	129.1	5.7	5.3	8.4	139.1	Moderate
97-254 COMP 80-86	80	86	8.58	6.78	154.1	1.66	0.02	1.64	51.3	91.9	81.9	1.8	1.6	3.0	91.9	Moderate
97-254 COMP 86-92	86	92	8.84	3	68.2	1.08	<0.01	1.08	33.8	56.1	46.1	1.7	1.4	2.0	56.1	Moderate
97-254 COMP 92-98	92	98	9.11	3.93	89.3	1.11	<0.01	1.11	34.7	81.8	71.8	2.4	2.1	2.6	81.8	Moderate
97-254 COMP 98-104	98	104	8.96	1.17	26.6	0.04	<0.01	0.04	1.3	29.4	19.4	23.5	15.5	21.3	29.4	Slight
97-254 COMP 104-110	104	110	9.49	1.29	29.3	0.4	<0.01	0.4	12.5	38.4	28.4	3.1	2.3	2.3	38.4	Slight
97-256 COMP 32-36	32	36	9.00	1.36	30.9	0.06	<0.01	0.06	1.9	46.8	36.8	25.0	19.6	16.5	44.9	Moderate
97-256 COMP 36-42	36	42	8.84	3.3	75.0	0.76	<0.01	0.76	23.8	69.0	59.0	2.9	2.5	3.2	45.3	Moderate
97-256 COMP 42-48	42	48	8.46	9.62	218.6	1.4	0.01	1.39	43.4	97.4	87.4	2.2	2.0	5.0	54.0	Moderate
97-256 COMP 48-54	48	54	8.66	6.74	153.2	1.07	<0.01	1.07	33.4	102.6	92.6	3.1	2.8	4.6	69.2	Moderate
97-256 COMP 54-60	54	60	8.72	10.28	233.6	0.4	<0.01	0.4	12.5	116.1	106.1	9.3	8.5	18.7	103.6	Moderate
97-256 COMP 60-66	60	66	8.72	9.78	222.3	1.4	<0.01	1.4	43.8	159.9	149.9	3.7	3.4	5.1	116.2	Moderate
97-256 COMP 66-72	66	72	8.58	5.62	127.7	1.91	0.02	1.89	59.1	100.9	90.9	1.7	1.5	2.2	41.8	Moderate
97-256 COMP 72-78	72	78	8.40	6.2	140.9	1.79	0.01	1.78	55.6	111.9	101.9	2.0	1.8	2.5	56.3	Moderate
97-256 COMP 78-84	78	84	8.67	5.51	125.2	1.53	0.01	1.52	47.5	94.2	84.2	2.0	1.8	2.6	46.7	Moderate
97-256 COMP 84-90	84	90	8.48	4.58	104.1	1.85	0.03	1.82	56.9	91.1	81.1	1.6	1.4	1.8	34.2	Moderate
97-256 COMP 90-96	90	96	8.37	2.22	50.5	2.15	0.03	2.12	66.3	44.5	34.5	0.7	0.5	0.8	-21.8	Moderate
97-256 COMP 96-102	96	102	8.42	1.58	35.9	2.93	0.02	2.91	90.9	69.0	59.0	0.8	0.6	0.4	-21.9	Strong
97-256 COMP 102-108	102	108	8.39	1.86	42.3	2.77	0.03	2.74	85.6	76.5	66.5	0.9	0.8	0.5	-9.1	Strong
97-258 COMP 60-66	60	66	8.02	5.77	131.1	0.02	<0.01	0.02	0.6	47.5	37.5	76.0	60.0	209.8	46.9	Slight
97-258 COMP 66-74	66	74	7.85	7.78	176.8	0.26	<0.01	0.26	8.1	92.7	82.7	11.4	10.2	21.8	84.6	Moderate
97-258 COMP 74-80	74	80	8.33	5.74	130.5	0.14	<0.01	0.14	4.4	88.2	78.2	20.2	17.9	29.8	83.8	Slight
97-258 COMP 80-86	80	86	8.18	6.74	153.2	0.23	<0.01	0.23	7.2	92.5	82.5	12.9	11.5	21.3	85.3	Slight
97-258 COMP 86-92	86	92	7.96	8.51	193.4	0.1	<0.01	0.1	3.1	129.0	119.0	41.3	38.1	61.9	125.9	Slight
97-258 COMP 92-98	92	98	8.09	3.89	88.4	<0.02	<0.01	0.01	0.3	70.9	60.9	236.3	203.0	294.7	70.9	Moderate
97-258 COMP 98-104	98	104	7.88	2.44	55.5	0.07	<0.01	0.07	2.2	52.7	42.7	24.1	19.5	25.4	50.5	Slight
97-258 COMP 104-110	104	110	7.92	5.93	134.8	1.11	<0.01	1.11	34.7	97.6	87.6	2.8	2.5	3.9	62.9	Moderate
97-258 COMP 110-116	110															